

RECEIVED
CENTRAL FAX CENTER
JUN 18 2007

AMENDMENTS TO THE CLAIMS

Please Cancel Claims 1-11, 17 and 18, and Amend Claims 12-16, 19 and 20, and add new Claims 21 and 33, as follows:

1. (Cancelled) A multi-layer article comprised of a fluoroelastomer polymer layer and a substrate wherein the bond between the layers is formed through a three stage molding technique where the substrate alone is first pre-cured to an incomplete state of cure in a mold at a temperature of 75 to 150 C, secondly an uncured fluoroelastomer film of less than or equal to 0.3 mm thickness is placed on the substrate and the layers are cured together in the mold at a temperature of 150 to 250 C and finally the article is removed from the mold and cured in an oven at a temperature of 100 to 180 C such that the cross linking of the layers forms a permanent bond between them, and wherein the fluoroelastomer comprises a monomer segment derived from an olefinic hydrocarbon.
2. (Cancelled) The multi-layer article of claim 1, wherein the fluoroelastomer is a copolymer including tetrafluoroethylene.
3. (Cancelled) The multi-layer article of claim 1, wherein the fluoroelastomer is a copolymer including vinylidene fluoride.
4. (Cancelled) The multi-layer article of claim 1, wherein the fluoroelastomer is a copolymer including hexafluoropropylene.
5. (Cancelled) The multi-layer article of claim 1, wherein the olefinic hydrocarbon is propylene.

6. (Cancelled) The multi-layer article of claim 1, wherein the olefinic hydrocarbon is ethylene.
7. (Cancelled) The multi-layer article of claim 1, wherein the substrate includes a non-fluorinated polymer.
8. (Cancelled) The multi-layer article of claim 7, wherein the non-fluorinated polymer comprises a thermoplastic polymer.
9. (Cancelled) The multi-layer article of claim 7, wherein the non-fluorinated polymer comprises a thermoplastic elastomer.
10. (Cancelled) The multi-layer article of claim 7, wherein the non-fluorinated polymer is selected from the group consisting of nitrile rubbers, ethylene-propylene-diene monomer rubbers, epichlorohydrin rubbers, ethylene-acrylate copolymer rubbers, polyamides, polyurethanes, polyolefins, and combinations thereof.
11. (Cancelled) The multi-layer article of claim 1, wherein the fluoroelastomer is a fluoroplastic.
12. (Currently Amended) A process for preparing a multi-layer article, comprising the steps of:
 - (a) ~~associating a polymer layer with~~ placing a substrate in a mold, ~~and wherein where~~ said substrate alone is first pre-cured to an incomplete state of cure in said mold at a temperature of 75 to 125 C,
 - (b) an uncured fluoroelastomer layer ~~film~~ of less than or equal to 0.3 mm thickness is placed on said pre-cured substrate of step (a) and said layers are cured together in said mold at a temperature of 150 to 225 C to form an intermediate article, and

S/N 10/711,607 (AMA No. 2004-309-SSI)

(c) removing said intermediate article of step (b) from said mold and curing it in an oven at a temperature of 100 to 150 C such that the cross linking of the layers forms a permanent bond between ~~them~~ said substrate and said fluoroclastomer layer and thereby forming said multi-layer article.

13. (Currently Amended) The process of claim 12, wherein said fluoroclastomer film layer is a copolymer derived from a monomer selected from a group consisting of tetrafluoroethylene, vinylidene fluoride, hexafluoropropylene and an olefinic hydrocarbon.

14. (Previously Amended) The process of claim 13, wherein said olefinic hydrocarbon is selected from a group consisting of ethylene and propylene.

15. (Currently Amended) The process of claim 12, wherein said substrate is selected from a group consisting of a non-fluorinated polymer ~~or~~ and a metal.

16. (Previously Amended) The process of claim 15, wherein said non-fluorinated polymer is selected from a group consisting of nitrite rubbers, ethylene-propylene-diene monomer rubbers, epichlorohydrin rubbers, ethylene-acrylate copolymer rubbers, polyanides, polyurethanes, polyolefins, and combinations thereof.

17. (Cancelled) The multi-layer article of claim 1, wherein the article is a fine bubble diffuser membrane as used in the waste water treatment industry.

18. (Cancelled) The multi-layer article of claim 1, wherein the article is a coarse bubble diffuser membrane as used in the waste water treatment industry.

19. (Currently Amended) The process of Claim 12, wherein said fluoroelastomer polymer layer comprises a fluoropolymer.

20. (Currently Amended) The process of Claim 12, wherein said fluoroelastomer film layer comprises a monomer segment derived from an olefinic hydrocarbon.

21. (New) The process of Claim 15, wherein said non-fluorinated polymer is selected from a group consisting of a thermoplastic polymer and a thermoplastic elastomer

22. (New) The process of Claim 12, wherein said fluoroelastomer layer is selected from a group consisting of a fine bubble diffuser membrane and a coarse bubble diffuser membrane.

23. (New) The process of Claim 12, wherein said fluoroelastomer is a fluoroplastic.

24. (New) A process for preparing a multi-layer article, comprising the steps of:

(a) placing a substrate in a mold, and wherein said substrate alone is first pre-cured to an incomplete state of cure in said mold at a temperature of 75 to 125 degrees C,

(b) an uncured fluoroelastomer layer of less than or equal to 0.3 mm thickness is placed on said pre-cured substrate of step (a) and said layers are cured together in said mold at a temperature of 150 to 250 degrees C to form an intermediate article, and

(c) removing said intermediate article of step (b) from said mold and curing it in an oven at a temperature of 100 to 180 degrees C such that the cross linking of the layers forms a permanent bond between said substrate and said fluoroclastomer layer and thereby forming said multi-layer article.

25. (New) The process of Claim 24, wherein said fluoroclastomer layer is a copolymer derived from a monomer selected from a group consisting of tetrafluoroethylene, vinylidene fluoride, hexafluoropropylene and an olefinic hydrocarbon.

26. (New) The process of Claim 25, wherein said olefinic hydrocarbon is selected from a group consisting of ethylene and propylene.

27. (New) The process of Claim 24, wherein said substrate is selected from a group consisting of a non-fluorinated polymer and a metal.

28. (New) The process of Claim 27, wherein said non-fluorinated polymer is selected from a group consisting of nitrite rubbers, ethylene-propylene-diene monomer rubbers, epichlorohydrin rubbers, ethylene-acrylate copolymer rubbers, polyamides, polyurethanes, polyolefins, and combinations thereof.

29. (New) The process of Claim 27, wherein said non-fluorinated polymer is selected from a group consisting of a thermoplastic polymer and a thermoplastic elastomer.

S/N 10/711,607 (AMA No. 2004-309-SSI)

30. (New) The process of Claim 24 wherein said fluoroelastomer layer is selected from a group consisting of a fine bubble diffuser membrane and a coarse bubble diffuser membrane.
31. (New) The process of Claim 24, wherein said fluoroelastomer layer comprises a fluoropolymer.
32. (New) The process of Claim 24, wherein said fluoroelastomer layer comprises a monomer segment derived from an olefinic hydrocarbon.
33. (New) The process of Claim 24, wherein said fluoroelastomer is a fluoroplastic.